

PERFORMANCE

VTS



5W-30 GTE

DATASHEET

TECHNICAL PHYSICAL DATA	
SAE GRADE	5W30
VISCOSITY 100 °C. cST.(ASTM D445)	12
VISCOSITY 40 °C. cST.(ASTM D445)	72
VISCOSITY INDEX, (ASTM D2270)	160
FLASH POINT °C. (ASTM D92)	225
FREEZING POINT °C. (ASTM D97)	-40
SULFATED ASH % by weight (ASTM D874)	0.5
TBN. (ASTM D-2896)	>6

RECOMMENDATIONS
MB 226.51
RENAULT RN 0720

DESCRIPTION

VTS 5W-30 GTE C4 HIGH QUALITY 100% SYNTHETIC LUBRICANT, BASED ON PAO AND GROUP III SYNTHETIC BASES WITH SPECIFIC LATEST GENERATION ADDITIVES, INDICATED FOR USE IN THE MOST MODERN GASOLINE AND DIESEL ENGINES REQUIRING THESE QUALITY LEVELS , ESPECIALLY THOSE OF THE RENAULT GROUP (RENAULT, DACIA, NISSAN) AND VEHICLES WITH RENAULT MECHANICAL

MAIN ADVANTAGES

- EXCELLENT LUBRICANT AND ANTI-WEAR PROPERTIES.
- GREAT RESISTANCE TO OXIDATION AND AGING.
- HIGH DETERGENT AND DISPERSANT POWER.
- GOOD PROTECTION AGAINST CORROSION.
- DECREASES OIL CONSUMPTION.
- USABLE IN WINTER AND SUMMER.
- REDUCES MAINTENANCE COST.
- LUBRICANT TO BE USED WHERE THE MANUFACTURER REQUESTS THESE QUALITY LEVELS.
- SUITABLE FOR ENGINES WITH EGR, TWC AND DPF PARTICULATE FILTER.

QUALITY LEVELS	
ACEA	C4
API	SM / CJ-4

Nerol, the Nerol logo and related marks are trademarks of Nerol Lubricants S.L. Used under licence.

This data sheet and the information it contains are believed to be accurate as of the date of printing. No warranty of representation, direct or implied, refers to the accuracy or completeness of the data and information contained in this publication. The data provided is based on standard tests under laboratory conditions and serves as a guide only. Users must ensure that they are using the latest version of this data sheet. It is the user's responsibility to evaluate and use the products safely, assess suitability for the intended application, and comply with all applicable laws and regulations. Safety Data Sheets are available for all products and should be consulted for appropriate information regarding storage, safe handling and transfer or sale of the product. Neither Nerol nor its subsidiaries have any liability for damages resulting from abnormal use of the material, failure to follow recommendations or dangers inherent in the nature of the material. All products, services and information provided are subject to our standard conditions of sale. Consult your local representative if you need more information